



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 382 620 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
21.01.2004 Bulletin 2004/04

(51) Int Cl.7: **C08F 214/26, C08F 14/18,**
C08F 16/24, H01B 3/44

(21) Application number: **03015360.5**

(22) Date of filing: **08.07.2003**

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PT RO SE SI SK TR
Designated Extension States:
AL LT LV MK

(30) Priority: **16.07.2002 IT MI20021561**

(71) Applicant: **Solvay Solexis S.p.A.**
20121 Milano (IT)

(72) Inventors:
• **Colalanna, Pasqua**
20100 Milano (IT)
• **Brinati, Giulio**
20139 Milano (IT)
• **Arcella, Vincenzo**
20014 Nerviano, Milano (IT)

(74) Representative: **Sama, Daniele, Dr. et al**
Sama Patents,
Via G.B. Morgagni, 2
20129 Milano (IT)

(54) **TFE Copolymers**

(57) Copolymers formed by TFE and FMVE containing FMVE in per cent by moles from 2.5% to 8%; the % TFE moles being the complement to 100% of the FMVE moles.

EP 1 382 620 A1

Description

[0001] The present invention relates to polymers used for the preparation of LAN cables (Local Area Network) for communications.

[0002] More specifically the present invention relates to fluorinated polymers used for the LAN cables preparation having improved properties, in particular the extrusion rate combined with improved electric insulation properties.

[0003] It is known in the prior art that LAN cables are obtained by extrusion and consist of a metal cable covered with a polymer, included fluorinated polymers, acting as insulator (primary cable). The LAN builds can also be formed by a series of interlaced primary cables, covered by a sheath or external jacket, constituted by a polymer equal or different from the polymer used for the primary cable. The obtained primary cable must have specific mechanical and electric properties.

[0004] For this ground it is required that the polymers used for the application in LAN cables show the following property combination:

- good chemical and thermal resistance;
 - good electric insulation properties (low dielectric constant and low dissipation factor);
 - good processability, as high extrusion speed with absence of melt-fracture and cracks of the extrusion cone;
 - maintenance on the finished cable of the following mechanical properties according to the UL 444 standard:
- stress and elongation at break determined at 23°C higher than or equal to, respectively, 17.2 MPa and 200%;
 - the stress and elongation at break after thermal aging at 232°C for 7 days must maintain at least 75% of their initial value.

[0005] It is known in the prior art the use in said applications of TFE copolymers with HFP and perfluoroalkylvinylethers, in particular TFE/HFP/FPVE or TFE/HFP/FEVE wherein TFE = tetrafluoroethylene, HFP = hexafluoropropene, FPVE = perfluoropropylvinylether, FEVE = perfluoroethylvinylether.

[0006] In USP 5,703,185 a TFE/HFP/FEVE copolymer for application in cables is described, which allows to reach higher extrusion speeds with respect to the TFE/HFP/FPVE copolymer. However even when the copolymer containing FEVE is used, on the basis of the results reported in the Examples of US patent, it is observed that at an extrusion speed of 800-900 m/min, the number of defects at the spark test is high, and there are from 3 to 4 sparks on a length of 14 km of cable. To obtain a lower number of defects in the same test, for example only one defect for the same cable length, it is necessary to reduce the wire speed under 800 m/min, in particular 732 m/min. Therefore to maintain good cable insulation properties it is necessary to reduce the extrusion speed and consequently the cable productivity. Therefore the known fluorinated copolymers of the prior art do not allow to obtain an improved combination of extrusion speed with improved electric insulation properties.

[0007] In EP 633,274 FMVE (perfluoromethylvinylether), TFE and perfluoroalkylvinylether terpolymers, in particular FPVE, are described, also used for preparing cables. The Applicant has found that by using said terpolymers there is not the above combination of improved properties since the extrusion rates are lower than 800 m/min and the defect number at the spark test is high.

[0008] The need was felt to have available polymers to be used in the preparation of LAN cables, in particular for preparing wire coating sheaths, which had the following property combination:

- good chemical and thermal resistance;
 - good electric insulation properties, in particular low dielectric constant and low dissipation factor;
 - good processability, as a combination of the following properties:
- high extrusion rate, of the order of about 800, in particular of the order of 900 m/min, or higher;
 - absence of melt-fracture and cracks of the extrusion cone;
 - spark test: at most two defects on 14 km of cable at extrusion rate of 900 m/min;
 - maintenance on the finished cable of the mechanical properties according to the UL 444 standard.

[0009] The Applicant has surprisingly and unexpectedly found fluorinated TFE-based polymers to be used in the LAN cable preparation which solve said technical problem.

[0010] An object of the present invention are copolymers formed by TFE and FMVE, having the following composition:

- FMVE in per cent by moles from 2.5% to 8%, preferably from 3.7% to 5.2%;

the % TFE moles being the complement to 100% of the FMVE moles.

[0011] Preferably the invention copolymers have the following properties:

- Melt Flow Index (ASTM D 1238) from 8 g/10 min to 50 g/10 min, preferably from 20 g/10 min to 40 g/10 min;
- the second melting temperature T(II) melt from 250°C to 300°C, preferably 275°C-289°C.

[0012] The invention copolymers show the following improved property combination:

- good chemical and thermal resistance;
- improved electric insulation property (low dielectric constant and low dissipation factor, even at extrusion rate > 800 m/min, and also > 900 m/min;
- improved processability, as high extrusion rate, higher than 800 m/minute, preferably of 900 m/min and even 1000 m/min, with absence of melt-fracture and cracks of the extrusion cone;
- spark test: at most two defects on 14 km of cable at the speed of 900 m/min;
- maintenance on the finished cable of mechanical properties according to the UL 444 standard.

[0013] The present invention fluoropolymers can be prepared by radical polymerization in aqueous or organic solvent. The emulsion polymerization in aqueous medium is carried out in the presence of a water-soluble inorganic radical initiator, such for example a peroxide, a percarbonate, a persulphate or azo compounds. Generally said radicals have sufficiently long half-life times, such that said compounds are present during the whole polymerization. In some cases a reducing agent can be added so to make easier the initiator decomposition. Said compounds can for example be iron salts. The initiator amount depends on the reaction temperature and on the reaction conditions. In particular said polymers are synthesized at a temperature in the range 60°C-90°C, preferably 70°C-80°C. Besides for the synthesis of said copolymers in particular a chain transfer agent is introduced so to regulate the polymer molecular weight, giving narrow molecular weight distributions. The used transfer agents can be ethane, methane, propane, chloroform, etc. The polymerization in aqueous phase takes place in the presence of fluorinated surfactants such for example perfluoroalkylcarboxylic acid salts (for example ammonium perfluorocaprylate, ammonium perfluorooctanoate), or other compounds such for example perfluoroalkoxybenzen-sulphonic acid salts, as described for example in EP 184,459. For the invention copolymer synthesis it is particularly advantageous to carry out the polymerization in aqueous phase in the presence of perfluoropolyethers, which can be added in the reaction medium under the form of aqueous emulsion in the presence of a suitable dispersing agent, as described in EP 247,379 or, preferably, in the form of aqueous microemulsion as described in USP 4,864,006.

[0014] Alternatively, the polymerization can be carried out in an organic solvent as described for example in USP 3,642,742. The polymerization initiator must be soluble in the reaction solvent. Said initiators can be alkylpercarbonates or perfluoroacylperoxides. The comonomers are generally fed to the reactor in the form of gaseous mixtures. The polymerization pressure is maintained constant by feeding the gaseous mixture TFE/fluoroalkylvinylether. The reaction pressures are in the range 15 Atm (1.5 MPa)-40 Atm (4 MPa), preferably in the range 20 Atm (2 MPa)-30 Atm (3 MPa).

[0015] The latex is coagulated and the recovered solid is dried and granulated. The granules are extruded in wire line to cover a metal conductor, for example copper. The extrusion temperature has a value generally at least 60°C higher than that of the second melting temperature of the polymer.

[0016] The Applicant has found that the monomeric composition range is critical to obtain TFE/FMVE copolymers having the required properties. Indeed by increasing the TFE amount in the copolymer over the limits indicated in the present invention, the mechanical properties determined on the cable (stress and elongation at break) do not satisfy the minimum values required by the UL 444 standard. Furthermore in this case the reached wire speed is not sufficiently high and there is a greater number of spark failures with respect to the cables covered with the invention copolymers.

[0017] The Applicant has found that by using TFE/FMVE/FPVE terpolymers, wherein the FMVE amount is in the amounts of the present invention, lower wire speeds are obtained with respect to the copolymers of the present invention. See the comparative Examples.

[0018] Furthermore, when in the invention copolymers the FMVE amount is in the preferred range, said copolymers are particularly suitable to obtain LAN cables since they have a dissipation factor lower than that of the polymers at present used (TFE/HFP/FEVE), so to obtain at high frequencies an improved insulation.

[0019] The results of the present invention are still more surprising if it is considered that in the prior art it is reported that the TFE/perfluoroalkylvinylethers copolymers are not suitable to be used for the above purposes. For example, in US patent SIRH130 it is stated that a TFE/FPVE copolymer has disadvantages when used in the wire covering since said copolymer is extrudable at high speeds only if the melt viscosity is lowered. In this way, according to the mentioned patent, there is the drawback to also decrease the stress crack resistance determined by the flex life. In USP SIRH130 it is also stated that when the stress crack resistance decreases, cracks on the cable insulation appear.

[0020] The Applicant has surprisingly and unexpectedly found that in the case of the TFE/FMVE copolymers of the present invention the good processability at high extrusion rates is maintained, even decreasing the melt viscosity.

[0021] Besides, the mechanical properties of the cable sheaths obtained with the copolymers of the present invention have been found to comply with the UL 444 standards.

[0022] The following Examples illustrate the invention without limiting the scope thereof.

5 EXAMPLES

[0023] The physical and mechanical properties of the copolymers illustrated in the Examples have been determined by the following methods:

10 Second melting temperature T(II)melt

[0024] The temperature is determined by a differential scanning calorimeter (Perkin Elmer). Approximately 10 mg of specimen are heated from room temperature up to 350°C with a 10°C/min rate. The specimen is maintained at 350°C for 5 min and then cooled to room temperature with a 10°C/min rate. The specimen is heated again up to 350°C with the same above modalities. During this phase the temperature corresponding to the maximum of the melting endo-thermal curve is recorded and indicated as second melting temperature.

Determination of the Melt Flow Index (MFI)

[0025] The determination is carried out according to the ASTM D 1238 standard.

Flex Life determination

[0026] The Flex Life is determined according to the ASTM D 2176-63T standard

25

Determination of the mechanical properties on the cable according to UL 444 standard

[0027] Various specimens of the manufactured cable are drawn and the mechanical properties of the insulating sheath are determined, before and after thermal aging for 7 days at 232°C. The mechanical properties are evaluated at the temperature of 23°C.

30

EXAMPLE 1

Preparation of a TFE/FMVE 96/4 polymer according to the invention and covering of a conductor with a sheath formed by the polymer

35

[0028] 13.9 litres of demineralized water, 128 g of a microemulsion prepared according to USP 4,864,006 are introduced in sequence in a 22 litre AISI 316 steel vertical autoclave, equipped with stirrer working at 400 rpm, after vacuum has been made. Then it is heated until reaching the temperature of 75°C. At this temperature 0.535 bar (5.35×10^4 Pa) of ethane and 3.16 absolute bar (3.16×10^5 Pa) of FMVE are fed. Then a gaseous TFE/FMVE mixture in molar ratio of TFE/FMVE of 24 until reaching a pressure of 21 absolute bar (2.1×10^6 Pa) is added by a compressor.

40

[0029] The composition of the gaseous mixture present in the autoclave head analyzed by gas chromatography. Before the reaction starts the gaseous phase results to be formed by the following compounds, in the indicated molar percentages: TFE 78.7%, FMVE 19.6%, ethane 1.7%. By a metering pump with a flow-rate of 170 ml/h, a KPS solution (potassium persulphate) 0.0103 M is fed. The polymerization pressure is maintained constant by feeding the aforesaid monomeric mixture and when 8,800 g of the above mixture have been fed, the monomer feeding is interrupted. The stirring is stopped and the pressure is let decrease until it reaches 6 absolute bar (6×10^5 Pa). The reactor is cooled at room temperature, the emulsion is discharged and it is coagulated with nitric acid 65%. The polymer is washed with water and then dried at 220°C. The nominal polymeric composition (calculated on the basis of the fed monomers), is the following: FMVE 6.5% by weight (4% by moles), TFE 93.5% by weight (96% by moles).

45

[0030] Table 1 reports the composition and some chemico-physical properties of the polymer.

[0031] The TFE/FMVE copolymer is extruded on a AWG 24 copper cable having a diameter of 0.51 mm, using a wire covering line wherein an extrusion technique is used with pipe die. The die is formed by a die having a diameter of about 8 mm and a tip having a diameter of about 5 mm. The thickness of the insulating sheath covering the conductor is of 0.15 mm, thus obtaining a draw down ratio of about 110. The length of the melted polymer cone coming out from the extrusion head is of about 5 cm and the distance from the cooling tank is at least of 10 cm. The temperature profile set in the extruder is the following:

55

$T_1 = 250^\circ\text{C}$
 $T_2 = 320^\circ\text{C}$
 $T_3 = 355^\circ\text{C}$
 $T_4 = 375^\circ\text{C}$
 $T_5 = 390^\circ\text{C}$
 $T_{\text{FLANGE}} = 390^\circ\text{C}$
 $T_{\text{BODY}} = 400^\circ\text{C}$
 $T_{\text{DIE HOLDER}} = 410^\circ\text{C}$
 $T_{\text{DIE}} = 420^\circ\text{C}$

[0032] The copper cable is preheated at a temperature from 90°C to 110°C . By using said conditions the cable can be stretched at rising rates by setting the suitable rotation speeds of the extruder screw until reaching polymer flow instability (oscillations, cone cracks, etc.).

[0033] The cable quality is monitored in line by a spark tester by which it is measured, on the basis of an applied potential difference, how many spark failures occur during the cable manufacture. Said spark failures occur in correspondence of defects in the insulating sheath. As reference length for detecting the spark failure number, 14 km of produced cable have been considered.

[0034] The reached maximum speed and the spark failure number occurring for 14 km of manufactured cable are reported in Table 2.

[0035] The cable is wound on winding coils. Various specimens of the manufactured cable are drawn and the mechanical properties of the insulating sheath, before and after thermal aging for 7 days at 232°C , as required by the UL 444 standard, are determined.

[0036] The results are reported in Table 3.

EXAMPLE 2 (comparative)

Preparation of a wire with sheath formed by a TFE/FMVE/FPVE terpolymer

[0037] The TFE/FMVE/FPVE terpolymer has been used, having composition, expressed in per cent by moles TFE 96.15% FMVE 3.5%, FPVE 0.35%, commercially known as Hyflon® MFA840, prepared according to US patent 5,463,006.

[0038] Granules of the terpolymer are extruded to obtain a wire covered as described in Example 1.

[0039] The composition and some chemico-physical properties of the polymer are reported in Table 1.

[0040] The reached maximum rate and the spark failure number occurring for 14 km of manufactured cable are reported in Table 2; the mechanical properties of the insulating sheath before and after thermal aging for 7 days at 232°C (UL 444 standard) are reported in Table 3.

EXAMPLE 3

Preparation of a TFE/FMVE 96.3/3.7 polymer and subsequent extrusion in wire line

[0041] The polymerization described in Example 1 is repeated except for the amount of the following components:

- ethane: 0.515 absolute bar (5.15×10^4 Pa);
- FMVE: 2.87 absolute bar (2.87×10^5 Pa);
- molar ratio TFE/FMVE in the fed monomeric mixture: 26.03;
- composition of the gaseous mixture present in the reactor head (analyzed by gaschromatography) before the reaction start, expressed in per cent by moles: TFE 82.5%, FMVE 16.0%, ethane 1.5%.

[0042] The nominal polymeric composition is the following: FMVE 6% by weight (3.7% by moles), TFE 94% by weight (96.3% by moles). The composition and some chemico-physical properties of the polymer are reported in Table 1.

[0043] The obtained granules are extruded to obtain a covered wire as described in Example 1.

[0044] The reached maximum rate and the spark failure number occurring for 14 km of manufactured cable are reported in Table 2; the mechanical properties of the insulating sheath before and after thermal aging for 7 days at 232°C (UL 444 standard) are reported in Table 3.

EXAMPLE 4

Preparation of a TFE/FMVE 95/5 polymer and subsequent extrusion in wire line

5 [0045] The polymerization described in Example 1 is repeated except for the amount of the following components:

- ethane: 0.44 absolute bar (4.4×10^4 Pa);
- FMVE: 4.1 absolute bar (4.1×10^5 Pa);
- molar ratio TFE/FMVE in the fed monomeric mixture: 19;
- 10 - composition of the gaseous mixture present in the reactor head before the reaction start, expressed in per cent by moles: TFE 73.3%, FMVE 25.5%, ethane 1.2%.

[0046] The nominal polymeric composition is the following: FMVE 8% by weight (5% by moles), TFE 92% by weight (95% by moles).

15 [0047] The composition and some chemico-physical properties of the polymer are reported in Table 1.

[0048] The obtained granules are extruded to obtain a cable covered as described in Example 1.

[0049] The reached maximum rate and the spark failure number occurring for 14 km of manufactured cable are reported in Table 2.

20 [0050] The mechanical properties of the insulating sheath before and after thermal aging for 7 days at 232°C (UL 444 standard) are reported in Table 3.

EXAMPLE 5 (comparative)

Preparation of a TFE/FMVE 98/2 polymer and subsequent extrusion in wire line

25 [0051] The polymerization described in Example 1 is repeated except for the amount of the following components:

- ethane: 0.64 absolute bar (6.4×10^4 Pa);
- FMVE: 1.52 absolute bar (1.52×10^5 Pa);
- 30 - molar ratio TFE/FMVE in the fed monomeric mixture: 49;
- composition of the gaseous mixture present in the reactor head before the reaction start, expressed in per cent by moles: TFE 89.3%, FMVE 9%, ethane 1.7%.

35 [0052] The nominal polymeric composition is the following: FMVE 3.3% by weight (2% by moles), TFE 96.7% by weight (98% by moles).

[0053] The composition and some chemico-physical properties of the polymer are reported in Table 1.

[0054] The obtained granules are extruded to obtain a cable covered as described in Example 1.

[0055] The reached maximum rate and the spark failure number occurring for 14 km of manufactured cable are reported in Table 2.

40 [0056] By using said polymer it has been observed that at rates higher than the maximum rate indicated in the Table of 100 m/min, the extrusion cone fracture takes place.

[0057] The mechanical properties of the insulating sheath before and after thermal aging for 7 days at 232°C (UL 444 standard) are reported in Table 3.

45 **EXAMPLE 6 (comparative)**

Preparation of a wire with sheath formed by a TFE/HFP/FEVE terpolymer according to USP 5,703,185

50 [0058] Granules of a TFE/HFP/FEVE terpolymer having the composition, expressed in per cent by moles, reported in Table 1, are extruded to obtain a covered cable as described in Example 1.

[0059] The composition and some chemico-physical properties of the polymer are reported in Table 1.

[0060] The reached maximum rate and the spark failure number occurring for 14 km of manufactured cable are reported in Table 2; the mechanical properties of the insulating sheath before and after thermal aging for 7 days at 232°C (UL 444 standard) are reported in Table 3.

55

EXAMPLE 7

Preparation of a TFE/FMVE 93.7/6.3 polymer and subsequent extrusion in wire line

5 **[0061]** The polymerization described in Example 1 is repeated except for the amounts of the following components:

- ethane: 0.405 absolute bar (4.05×10^4 Pa);
- FMVE: 4.5 absolute bar (4.5×10^5 Pa);
- molar ratio TFE/FMVE in the fed monomeric mixture: 14.87;
- 10 - composition of the gaseous mixture present in the reactor head before the reaction start, expressed in per cent by moles: TFE 72.6%, FMVE 25.8%, ethane 1.6%.

[0062] The nominal polymeric composition is the following: FMVE 10.04% by weight (6.3% by moles), TFE 89.96% by weight (93.7% by moles).

15 **[0063]** The composition and some chemico-physical properties of the polymer are reported in Table 1.

[0064] The obtained granules are extruded to obtain a cable covered as described in Example 1.

[0065] The reached maximum rate and the spark failure number occurring for 14 km of manufactured cable are reported in Table 2.

20 **[0066]** The mechanical properties of the insulating sheath before and after thermal aging for 7 days at 232°C (UL 444 standard) are reported in Table 3.

Comments on the results of the Examples

25 **[0067]** The Tables show that by increasing the TFE amount in the copolymer, see Table 3, beyond the present invention limits, see the Example 5 (comparative) (TFE = 98% by moles) the mechanical properties determined on cable (stress and elongation at break for Example 5 (comparative)) are lower than the corresponding minimum values required by the UL 444 standard. Besides, the speed reached in wire line is very low (Table 2) with a high incidence of spark failures.

30 **[0068]** Table 2 shows that the cable obtained from the TFE/FMVE/FPVE terpolymer is extruded at a lower wire speed with respect to the cable obtained with the copolymer according to the present invention.

35

40

45

50

55

Table 1

Composition and chemico-physical properties of the copolymers of Examples 1-5				
Examples	Polymer composition		T(II)melt (°C)	MFI (g/10')
	Monomers	% by moles		
1	TFE/FMVE	96/4	286.5	22
2 comp.	TFE/FMVE/FPVE	96.15/3.5/0.35	285	22
3	TFE/FMVE	96.3/3.7	290	22
4	TFE/FMVE	95.0/5.0	274	23
5 comp.	TFE/FMVE	98/2	305	21
6 comp.	TFE/HFP/FEVE	91.7/8/0.3	-	-
7	TFE/FMVE	93.7/6.3	264	21

Table 2

Wire speed and spark test (failures/14 km) of the polymers of the Examples used to cover AWG 24 cables, having a diameter of 0.81 mm

Examples	Wire speed (m/min)	Spark test Spark failures /14 km
1	900	2
2 comp.	600	3
3	900	2
4	900	2
5 comp.	100	2*
6 comp.	900	4
7	900	2

* frequent cracks of the extrusion cone

Table 3

Examples	Extruded wire		Wire after aging.	
	Stress at break (MPa)	Elong. at break (%)	Stress at break (MPa)	Elong. at break (%)
1	18.2	210	17.8 (98%)	214
2 comp.	18	200	17 (94%)	200
3	17.2	260	14 (81%)	240
4	20	220	17.6 (88%)	200
5 comp.	13.3*	60**	-	-

* value of stress at break lower than the minimum required by the UL 444 standard.

** value of elongation at break lower than the minimum (200%) required by the UL 444 standard.

Claims

1. Copolymers formed by TFE and FMVE, having the following composition:

- 5 - FMVE in per cent by moles from 2.5% to 8%, preferably from 3.7% to 5.2%;

the % TFE moles being the complement to 100% of the FMVE moles.

2. Copolymers according to claim 1 having the following properties:

10

- Melt Flow Index (ASTM D 1238) from 8 g/10 min to 50 g/10 min, preferably from 20 g/10 min to 40 g/10 min;
- the second melting temperature T(II) melt from 250°C to 300°C, preferably 275°C-289°C.

3. Use of the copolymers according to claims 1-2 to prepare by extrusion sheaths for cables.

15

4. Use according to claim 3 wherein the cables are LAN cables.

5. Wires having sheaths formed by the polymers of claims 1-2.

20

25

30

35

40

45

50

55



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 03 01 5360

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 979 832 A (AUSIMONT SPA) 16 February 2000 (2000-02-16) * paragraphs [0029], [0032]; claims 14-16 * ---	1-5	C08F214/26 C08F14/18 C08F16/24 H01B3/44
X	US 5 760 151 A (ATEN RALPH MUNSON ET AL) 2 June 1998 (1998-06-02) * column 8, line 65 - column 9, line 15 * ---	1-5	
X	EP 0 818 489 A (AUSIMONT SPA) 14 January 1998 (1998-01-14) * page 3, line 52-55 * * page 6, line 26,27 * ---	1-5	
X	EP 0 633 274 A (AUSIMONT SPA) 11 January 1995 (1995-01-11) * page 1, line 1,2; table 1 * ---	1-5	
A,D	US 4 864 006 A (VISCA MARIO ET AL) 5 September 1989 (1989-09-05) * the whole document * -----	1-5	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C08F H01B
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 25 August 2003	Examiner Zeslawski, W
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons</p> <p>& : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03 02 (P04001)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 03 01 5360

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

25-08-2003

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0979832 A	16-02-2000	IT M1981880 A1	11-02-2000
		BR 9903612 A	26-12-2000
		EP 0979832 A1	16-02-2000
		JP 2000072826 A	07-03-2000
		US 2003096930 A1	22-05-2003
		US 2002065372 A1	30-05-2002
US 5760151 A	02-06-1998	CN 1193328 A	16-09-1998
		DE 69602607 D1	01-07-1999
		DE 69602607 T2	28-10-1999
		EP 0845009 A1	03-06-1998
		JP 2002509557 T	26-03-2002
		WO 9707147 A1	27-02-1997
		US 5932673 A	03-08-1999
EP 0818489 A	14-01-1998	IT M1961412 A1	09-01-1998
		DE 69716352 D1	21-11-2002
		DE 69716352 T2	20-02-2003
		EP 0818489 A2	14-01-1998
		JP 10101922 A	21-04-1998
		US 5942572 A	24-08-1999
EP 0633274 A	11-01-1995	IT 1264661 B1	04-10-1996
		AT 148474 T	15-02-1997
		CA 2127296 A1	06-01-1995
		DE 69401621 D1	13-03-1997
		DE 69401621 T2	10-07-1997
		DK 633274 T3	17-02-1997
		EP 0633274 A1	11-01-1995
		ES 2097579 T3	01-04-1997
		GR 3022893 T3	30-06-1997
		JP 7304832 A	21-11-1995
		MX 9405089 A1	31-01-1995
		RU 2141489 C1	20-11-1999
		US 5463006 A	31-10-1995
US 4864006 A	05-09-1989	IT 1204903 B	10-03-1989
		AT 66937 T	15-09-1991
		AU 601408 B2	13-09-1990
		AU 7217787 A	07-01-1988
		BR 8702109 A	09-02-1988
		CA 1281489 C	12-03-1991
		CN 87103869 A ,B	06-01-1988
		CS 8703010 A3	16-12-1992
		DD 262433 A5	30-11-1988
		DE 3772640 D1	10-10-1991

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 03 01 5360

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

25-08-2003

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4864006 A		EG 18792 A	28-02-1994
		EP 0250767 A1	07-01-1988
		ES 2025574 T3	01-04-1992
		FI 871902 A ,B,	27-12-1987
		GR 870659 A1	28-08-1987
		IL 82309 A	10-03-1991
		IN 167721 A1	15-12-1990
		JP 2562890 B2	11-12-1996
		JP 63008406 A	14-01-1988
		KR 9410337 B1	22-10-1994
		NO 871771 A ,B,	28-12-1987
		PT 84792 A ,B	01-05-1987
		RU 2026308 C1	09-01-1995
		TR 23920 A	11-12-1990
		ZA 8702891 A	25-11-1987

EPC FORM P449

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82